

Обозначение металлов по стандартам разных стран

Стандарт №	Италия	Франция	Германия	Великобритания	Европа	США	Япония	Торговое название
0.7040	EN-GJS 400-15 GS400	EN-GJS 400-15 FGS 400-15 FGS 400-12	EN-GJS 400-15 GGG-40	EN-GJS 400-15 Grade 420/12	EN-GJS 400-15	ASTM A 536 (60-40-18)	FCD 400	
1.0432			C 21			ASTM A 105 K03502 ASTM A181 (60,70)		
1.0619	GP240GH	GP240GH	GP240GH	GP240GH AL 1	GP240GH	ASTM A 216 (WBC)	SCPH 1	
1.4006 1.4008	X12Cr13 GX7CrNiMo12-1 X12Cr13KG; KW	X12Cr13 GX7CrNiMo12-1 Z 10 C 13	X12Cr13 GX7CrNiMo12-1 410 S 21 1630 grade A EN 56 A	X12Cr13 GX7CrNiMo12-1 GX8CrNi13	X12Cr13	ASTM A 743 Ca15 AISI 410 UNS J91171 ASTM A 217 CA-15	SUS 410	
1.4301	X5CrNi18-10	X5CrNi18-10	X5CrNi18-10	X5CrNi18-10 304 S 31	X5CrNi18-10	AISI 304 ASTM A 358(304) SAE 304 UNS S30400	SUS 304	
1.4306 1.4309	X2CrNi19-11 GX2CrNi19-11	X2CrNi19-11 GX2CrNi19-11 Z 3 CN 19.10 M	X2CrNi19-11 GX2CrNi19-11	X2CrNi19-11 GX2CrNi19-11 304 C 12 304 S 11 1631 grade C	X2CrNi19-11 GX2CrNi19-11	ASTM A 351 CF3 AISI 304 L UNS J92500	SUS 304 L	
1.4308	GX5CrNi9-10	GX5CrNi9-10 Z 6 CN 18.10 M Z 6 CN 19.9 M	GX5CrNi9-10	GX5CrNi9-10 304 C 15 1631 grade A	GX5CrNi9-10	ASTM A 351 CF8 SAE 304 H UNS J 92600	SCS 13	
1.4313 1.4317	X3CrNiMo13-4 GX4CrNi13-4	X3CrNiMo13-4 GX4CrNi13-4 Z 6 CN 13.4 M Z 6 CN 13-04	X3CrNiMo13-4 GX4CrNi13-4	X3CrNiMo13-4 GX4CrNi13-4	X3CrNiMo13-4 GX4CrNi13-4	ASTM A 743 CA6NM UNS J91540 13Cr-4Ni Spec SAE S41500	SCS 5 SCS 6	
1.4401	X5CrNiMo17-12-2	X5CrNiMo17-12-2	X5CrNiMo17-12-2	X5CrNiMo17-12-2	X5CrNiMo17-12-2	AISI 316 UNS S31600 ASTMA A 358 (316) SAE 316	SUS 316	
1.4404	X2CrNiMo17-12-2 X 2 CrNiMo 17-12	X2CrNiMo17-12-2 Z 3 CN 19.10 M	X2CrNiMo17-12-2 X2CrNiMo17-13-2	X2CrNiMo17-12-2 316S 11	X2CrNiMo17-12-2	ASTM A 351 CF3M AISI 316 L UNS J92700	SUS 316 L	
1.4408	GX5CrNiMo19-11-2	GX5CrNiMo19-11-2	GX5CrNiMo19-11-2	GX5CrNiMo19-11-2 845 grade B 316 C 16 316 C 16LT196 1632 grade B ANC 4 grade B	GX5CrNiMo19-11-2	ASTMA A 351 (CF8M)	SCS 14	
1.4460	X3CrNiMoN27-5-2	X3CrNiMoN27-5-2 Z 5 CN 27-05 Az	X3CrNiMoN27-5-2	X3CrNiMoN27-5-2	X3CrNiMoN27-5-2	ATM 890 CD6NM AISI 329 UNS J 93371 SAE 32900	SUS 329J1	Duplex
1.4462	X2CrNiMoN22-5-3	X2CrNiMoN22-5-3 318 S 31	X2CrNiMoN22-5-3	X2CrNiMoN22-5-3	X2CrNiMoN22-5-3	UNS S31803 ASTM A 182 F60	SUS 329J3L	Duplex Cr22
1.4470	GX2CrNiMoN22-5-3	GX2CrNiMoN22-5-3	GX2CrNiMoN22-5-3	GX2CrNiMoN22-5-3	GX2CrNiMoN22-5-3	ATMA A 890 CD3MN UNS J92205		Duplex
1.4500		Z 3 NCDU 25.20 M	GX7NiCrMo- CuNb25-20	332 C 11		ASTM A 351 CN7M UNS N08700 ASTM B 672		Duplex
1.4501	X2CrNiMo- CuWN25-7-4	X2CrNiMo- CuWN25-7-4	X2CrNiMo- CuWN25-7-4	X2CrNiMo- CuWN25-7-4	X2CrNiMo- CuWN25-7-4	ASTM A 182 F55 UNS S32760		Super Duplex Cr25
1.4535			X90CrCoMoV17			ASTM 351 CF3M Mo>2.5		
1.4542	X5CrNiCuNb16-4	X5CrNiCuNb16-4 Z 7 CNU 15-05	X5CrNiCuNb16-4	X5CrNiCuNb16-4	X5CrNiCuNb16-4	ASTMA A747 CB7Cu1 AISI 630 UNS S17400 17-4 PH	SUS 630	
1.4539	X1NiCrMoCu25-20-5	X1NiCrMoCu25-20-5 Z 2 NCDU 25-20	X1NiCrMoCu25-20-5	X1NiCrMoCu25-20-5 904 S 13	X1NiCrMoCu25-20-5	UNS N 08904 AISI 904 L	URANUS B6	
1.4547 1.4529	X1NiCrMoCu25-20-7 X1NiCrMoCu20-18-7	X1NiCrMoCu25-20-7 X1NiCrMoCu20-18-7	X1NiCrMoCu25-20-7 X1NiCrMoCu20-18-7	X1NiCrMoCu25-20-7 X1NiCrMoCu20-18-7	X1NiCrMoCu25-20-7 X1NiCrMoCu20-18-7	ASTM A 182 (F904L) ASTMA351 CK3MCuN SAE N08926 UNS J93254	6MO	
1.4825 1.4826	GX25CrNiSi18-9 GX40CrNiSi22-10	GX25CrNiSi18-9 GX40CrNiSi22-10	GX25CrNiSi18-9 GX40CrNiSi22-10 GX40CrNiSi22-9	GX25CrNiSi18-9 GX40CrNiSi22-10	GX25CrNiSi18-9 GX40CrNiSi22-10	ASTM A 297 NF HF-30 (spec) UNS J92603	SCH 12	
1.4848	GX40CrNiSi25-20 G X 40 CrNi 26 20	GX40CrNiSi25-20	GX40CrNiSi25-20	GX40CrNiSi25-20 310 C 40 310 C 45 1648 grade F	GX40CrNiSi25-20	ASTM A 608 (HF-30) ASTM A 297 HK30 ACI HK-30 ASTM A 351 HK30 UNS J94224	SCH 21 SCH 22	
1.4849 1.4865	GX40NiCrSiNb38-19 GX40NiCrSi38-19 G X 50 NiCr 39 19	GX40NiCrSiNb38-19 GX40NiCrSi38-19	GX40NiCrSiNb38-19 GX40NiCrSi38-19 GX40NiCrSi38-18 GX40NiCrSiNb38-18	GX40NiCrSiNb38-19 GX40NiCrSi38-19 GX40NiCrSi38-19 330 C 11 331 C 40 4238 grade H 1 C 4238 grade H 2 C	GX40NiCrSiNb38-19 GX40NiCrSi38-19	ASTM A 297 HU ACI HT-30 ASTM A 351 (HT30) UNS N08004	SCH 15 SCH 16	
2.4360		NU 30	NiCu 30 Fe DIN 17743	NA 13 BS307276		UNS N04400 ASTM B 127 ASME SB127		MONEL 400
2.4602			NiCr 21 Mo 14 W			ASTM A 494 CX2MW UNS N06022		HASTELLOY C-22 INCONEL alloy 622

Стандарт №	Италия	Франция	Германия	Великобритания	Европа	США	Япония	Торговое название
2.4660			NiCr 20 CuMo			UNS N08020		Alloy 20
2.4856	NiCr22Mo9Nb	NiCr22Mo9Nb	NiCr22Mo9Nb DIN 17744	NiCr22Mo9Nb NA 21 BS3076	NiCr22Mo9Nb	ASTM A 358 (N 08020) ASTM A 494 CW6MC ASTMA B 443-4 UNS N26625	NCF 625 NCF625TP NCF625TB	INCONEL alloy 625
						ASTM A 890 CD4MCu UNS J93370		Duplex
						ASTM A 351 (CD4MCu) ASTM A 890 CE3MN		Duplex
				BS 1400 AB2		ASTM B 148 UNS C95800		
				BS 1400 G2		ASTM B 143 2B SAE 621		
	CuAl10Fe5Ni5-C UNI 5275		G-NiAlBzF60 DIN 1714	BS 1400 AB2		ASTM B 148 9D SAE 701C UNS C95500		
	G-CuAl 9Fe3 UNI 5273		G-NiAlBzF50 DIN 1714	BS 1400 AB1		ASTM B 148 9A SAE 68 A UNS C95200		
	CuSn10-C UNI 1013-1		G-SnBz10 DIN 1705	BS 1400 PB3		ASTM B 427 SAE 63		
	CuSn10Zn2 UNI 7013-6		G-Rg 10 DIN 1705	BS 1400 G1		UNS C90700 ASTM B 584 SAE 620		
	CuSn5ZnPb5-C UNI 7013-8		G-Rg 5 DIN 1705	BS 1400 LG2		UNS C90500 SAE 40		